

BULK MATERIAL ASBESTOS ANALYSIS REPORT

Client:   
St. Paul, MN 55117

Report Date: 5/19/11

Project No.: 1102171

Client Project: 1889 East Montana

Date Received: 5/19/11


Date Analyzed: 5/19/11

SAMPLE NO.	LAB NO.	SAMPLE DESCRIPTION	ASBESTOS TYPE (%)	OTHER MATERIAL (%)
1	1102171 - 1	Transite Sample Gray, Cementitious Homogeneous	15% Chrysotile	85% Nonfibrous

The analysis was performed in accordance with current U.S. Environmental Protection Agency (USEPA) protocols, "Method for the Determination of Asbestos in Bulk Building Materials," EPA 600/R-93/116, 1993. All reported percentages are by visual estimates. In the case of nonhomogeneous samples, each material or layer is analyzed separately and the reported percentages are based on the total sample as received, unless other instructions are received from the client. The samples were received in acceptable condition.

NVLAP Laboratory Accreditation Number: 102081-0

ANALYST:



Todd Giorgi  
Microscopist

- This document cannot be duplicated, except in its entirety, without the express written authorization from LEGEND TECHNICAL SERVICES, INC.
- This report must not be used to claim product endorsement by NVLAP or any agency of the U.S. Government.
- This report relates only to the above items tested.



Faint, illegible text spanning the width of the page, appearing as a header or introductory paragraph.

A large block of extremely faint and illegible text, likely the main body of a letter or document.

A short, faint line of text, possibly a signature or a closing phrase.

Another short, faint line of text, possibly a second signature or a reference line.

The final line of faint text at the bottom of the page, possibly a footer or a date.